

AEROSPACE COATINGS

Used to accelerate cure time

of Jet Glo Conventional.

drying times on stripes,

registration numbers, logos and panel repair re-painting.

CM08181HR is most generally used for quick

<u>ADVANTAGES</u>

PRODUCT DATA

Jet Glo[®] Accelerator

DESCRIPTION

CM0120975 is a conventional urethane accelerator intended to speed cure and tape time of Jet Glo Conventional. Urethane accelerators are very reactive and great care must be used in the quantity added.

Excess CM0120975 Accelerator can cause gassing (solvent pop and microblisters), loss of gloss and haze.

COATING PROPERTIES

Weight per Gallon: 8.32 Specific Gravity: 1.00

VOC: 8.23 lb./gal (987 g/L)

Workable Pot Life: 1 Hour

(Limited) 2-3 Hours Gelled

SHELF LIFE

Shelf Life is only applicable for materials stored in unopened and undamaged containers.

Minimum Storage Temp. 40°F / 4°C Maximum Storage Temp. 90°F / 32°C

CM0120975: 3 years

MIXING INSTRUCTIONS

Maximum dosage should be ¼ fluid ounce per ½ gallon of admixed material. This will usually speed the tape time to approximately 2-3 hours at 75°F (24°C). Most commonly used for quick drying times on stripes, registration numbers and logos.

Do not use for overall base colors, epoxy primers, metallic paint, or in high temperature or high humidity conditions.

PRODUCT INFORMATION

Product Data Sheets are periodically updated to reflect new information relating to the product. It is important that the customer obtain the most recent Product Data Sheet for the product being used. The information, rating, and opinions stated here pertain to the material currently offered and represent the results of tests believed to be reliable. However, due to variations in customer handling and methods of application, which are not known, or under our control, The Sherwin–Williams Company cannot make any warranties as to the end result.





Sherwin–Williams Aerospace Coatings • 415 E. Commerce Street • Andover, KS 67002 Tel: 316.733.7576 • Toll Free: 888.888.5593 • Fax: 316.733.6990 www.swaerospace.com Revision 4, 05/01/2009, Page 1 of 1